

DRYWALL ADHESIVE

- Accepted by FHA-HUD
- Meets ASTM C557
- Tested in accordance with ASTM E72 for racking and Shear
- See ICC-ES Evaluation Report No. ESR-2065

SPECIAL CHARACTERISTICS

- Increases Structural Strength
- Bridges Framing Defects of up to 3/8"
- Requires up to 66% Fewer Nails or Screws
- Will Not Stain Vinyl-Faced Gypsum board
- Reduces Impact Sound caused by Loose boards
- Reduces Spackling & Sanding
- Reduces Unattractive Nail Pops

DIRECTIONS

Ramset Drywall Adhesive is designed for installing regular and vinyl-faced gypsum wallboard to wood and steel framing members using up to 66% less fasteners. It is also recommended for bonding gypsum wallboard to clean, unpainted sound substrates. APPLY a continuous 3/8" bead to clean framing members with hand caulking gun. Where two boards butt on a framing member apply zigzag bead so adhesive will contact both boards. Use 1/8" bead on steel studs.

DO NOT APPLY ADHESIVE MORE THAN 20 MINUTES BEFORE INSTALLING GYPSUM WALLBOARD. Do not use warped boards. Follow nailing schedule per Gypsum Association manual (GA-201-85).

WALLS: Place board on framing and press firmly into place. Use fasteners 16" o.c. around perimeter of board. NO FASTENERS ARE REQUIRED IN THE FIELD OF THE BOARD. **CEILING:** Follow wall instructions except, in the field of the board use fasteners 24" o.c. **COVERAGE:** 3/8" bead-38 lineal feet, 1/4" bead-88 lineal feet, 1/8" bead-352 lineal feet. For best results store adhesives at 70°F. for at least 24 hours before using. Do not apply below 40°F. Do not store above 100°F. Clean tools and remove adhesive smears with mineral spirits, exercising safe practices.

May be used with Foamboard at temperatures below 90°F. Flashing is recommended.

Clean up: Clean tools and adhesive smears with mineral spirits, exercising safe practices.

PACKAGING INFORMATION:	ITEM NO.	SIZE	PACKED	WEIGHT
	DA100	28 oz ctg	12/ Carton	29 lbs./Carton

TYPICAL PHYSICAL PROPERTIES & TECHNICAL INFORMATION

BASE: Synthetic Rubber	STORAGE TEMP: 60°F to 80°F with cross ventilation
TYPE: Solvent Base	APPLICATION TEMP: 40°F to 100°F
COLOR: Tan	SERVICE TEMP: -20F to 170°F
WEIGHT/GALLON: 9.2 lbs	FLASH POINT: Less than 0°F
SOLIDS CONTENT: 70%	WATER RESISTANCE: Excellent
CONSISTENCY: Medium Mastic	MILDEW RESISTANCE: Excellent
OPEN TIME: 20 Minutes Maximum at 75° and 50% relative humidity.	COVERAGE: Up to 39 linear ft/ctg using 3/8" bead
DRY TIME: 24-48 hours at 75°F and 50% relative humidity.	SHELF LIFE: 12 months

ASTM C 557 STANDARD SPECIFICATION FOR FASTENING GYPSUM WALLBOARD TO WOOD FRAMING.

	TEST	RESULTS	REQUIREMENTS
SHEAR STRENGTH:	24 Hour	32 psi	10 psi
	14 Days	60 psi	40 psi
TENSILE STRENGTH:	24 Hours	21 psi	15 psi
	14 Days	73 psi	25 psi

DRYWALL ADHESIVE

DANGER!
EXTREMELY FLAMMABLE LIQUID AND VAPOR.
VAPORS MAY CAUSE FLASH FIRE.
HARMFUL OR FATAL IF SWALLOWED.

PRECAUTIONS: MAY AFFECT THE BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN, NOSE AND THROAT IRRITATION. HARMFUL OR FATAL IF SWALLOWED. MAY BE HARMFUL IF ABSORBED THROUGH THE SKIN. Do not puncture or incinerate (burn) container. Exposure to heat or prolonged exposure to sun may cause bursting. Do not expose to heat or store at temperatures above 100F. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

Vapors may ignite explosively. Keep away from heat, sparks and flame. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors, and other sources of ignition during use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation.

Use only with adequate ventilation. Do not breathe dust, vapors or spray mist. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience difficult breathing, eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA approved) or leave the area. Close container after each use. Avoid contact with eyes, skin and clothing.

WARNING: This product contains silica, quartz, a chemical known to the state of California to cause cancer.

NOTICE: Reports have associated repeated and prolonged occupational exposure to solvents with permanent brain and nervous system damage.

First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes. For skin contact, wash thoroughly with soap and water. If swallowed, or continued difficulty breathing, immediately call a physician, hospital emergency room or poison control center.

KEEP OUT OF REACH OF CHILDREN.
FOR PROFESSIONAL OR INDUSTRIAL USE ONLY.
IF YOU DO NOT UNDERSTAND, OR CANNOT READ, ALL DIRECTIONS,
CAUTIONS AND WARNINGS, DO NOT USE THIS PRODUCT.

Notice to Purchaser: NO WARRANTIES, EXPRESS OR IMPLIED ARE MADE INCLUDING MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL ITW RAMSET, A DIVISION OF ILLINOIS TOOL WORKS INC., OR ITS AFFILIATES ("ITW RAMSET") BE LIABLE FOR ANY LOSS OR DAMAGE ARISING FROM THE PURCHASE, USE, OR INABILITY TO USE THIS PRODUCT, OR FOR ANY SPECIAL, INDIRECT INCIDENTAL, OR CONSEQUENTIAL DAMAGES. THE USER MAY SEND A SAMPLE OF PRODUCT TO ITW RAMSET FOR TESTING. IF SUCH TESTING PROVES A PRODUCT DEFECT, THE USER'S SOLE AND EXCLUSIVE REMEDY IS EITHER REIMBURSEMENT OF THE PURCHASE PRICE OF THE PRODUCT OR REPLACEMENT OF THE CONTAINER OF PRODUCT. NO FABRICATOR, INSTALLER, DEALER, AGENT OR EMPLOYEE OF ITW RAMSET HAS THE AUTHORITY TO MODIFY THE OBLIGATIONS OR LIMITATION OF THIS WARRANTY. This warranty gives you specific legal rights, and you may also have other rights which vary from state to state; therefore, some of the limitations stated above may not apply to you. It is to your benefit to save your documentation upon purchase of a product.

Please direct all inquiries regarding performance of this product to: **ITW RAMSET**
700 High Grove Blvd
Glendale Heights, IL 60139
Phone: 1.800.726.7386 Fax: 630.893.1291
www.ramset.com